Reactive primer for cementitious substrates

Properties

Area of application

- Medium viscosity
- Medium penetration capacity

- Primer resin for concrete and cement screed

Hardener dosages

| Temperature | SILIKAL® BPO % by weight * | Pot life approx. min. | Hardening time approx. min. |
|-------------|-------------------------------|--------------------------|-----------------------------|
| +5 °C | 6.0 | 15 | 50 |
| +10 °C | 5.0 | 15 | 40 |
| +20 °C | 3.0 | 12 | 35 |
| +30 °C | 2.0 | 12 | 30 |

^{*} The amount of SILIKAL® BPO is always calculated with reference to the amount of resin.

Advice on application

- SILIKAL® BPO must be stirred in until it is fully dissolved (approx. 1 minute) and the mixture must be used immediately.
- The mixture must be applied such that it forms a film. If the mixture penetrates in the substrate, it must be reworked wet in wet.
- Curing and adhesion tests must generally be performed.
- Puddling must be avoided during application.
- Always use primers as clear resin they should never be filled or pigmented.

Guideline recipe

| No. | Component | Guideline recipe (% by weight) | Comment | Batch for 10 litre bucket |
|-----|---------------|-----------------------------------|--|---|
| 1 | SILIKAL® R 52 | 100 % | | 10 kg |
| | Total: | 100 % | Average consumption: 400 g/m ² | 10 kg |
| 2 | SILIKAL® BPO | 2 – 6 % with ref. to no. 1 | | See "Hardener dosages" table for quantities |



Reactive primer for cementitious substrates

Characteristics as delivered

| Property | Approx. value |
|-------------------------|------------------------|
| Viscosity, +20 °C | 300 mPa ⋅ s |
| Density, +20 °C | 0.98 g/cm ³ |
| Application temperature | +5 °C to +30 °C |

CE marking

| CE | | | | |
|---------------------------------|--------|--|--|--|
| 09 | | | | |
| SILIKAL GmbH | | | | |
| Ostring 23 · 63533 Mainhausen | | | | |
| www.silikal.com | | | | |
| R52-001 | | | | |
| EN 13813:2002 | | | | |
| Synthetic resin screed | | | | |
| for application in buildings | | | | |
| Reaction to fire | E, | | | |
| Release of corrosive substances | SR | | | |
| Wear resistance | ≤ AR1 | | | |
| Bond strength | ≥ 1.5 | | | |
| Impact resistance | ≥ IR 4 | | | |



0

Other applicable documents

SILIKAL® BPO Data sheet BPO
General notes Technical documentation MMA
Safety data sheets All used Silikal products

The information in this data sheet replaces all previous information about the product and its application. The application instructions as well as the technical data of the product are only guidelines. The buyer is responsible for the application and claims of third parties.



Ostring 23 · 63533 Mainhausen · Germany Phone: +49 (0) 61 82 / 92 35-0 mail@silikal.de · www.silikal.de

35