

SILIKAL® RF 6200 / Base

Reactive, pigmented, slightly elasticised top coat.

Alternatively, also available as non-pigmented, pre-filled base variant.

Properties

- Medium viscosity
- Very good self-levelling properties
- Pre-filled and pigmented ready to use or just pre-filled
- Slightly flexible when cured

Area of application

- Coloured top coat for broadcasted main coats indoors and outdoors

Hardener dosages

Temperature	SILIKAL® BPO % by weight *	Pot life approx. min.	Hardening time approx. min.
0 °C	6.0	20	50
+10 °C	4.0	20	45
+20 °C	2.0	15	40
+30 °C	1.0	12	30

* The amount of SILIKAL® BPO is always calculated with reference to the amount of resin.

Advice on application

- First SILIKAL® RF 6200 needs to be stirred and only then SILIKAL® BPO should be added and mixed until it has dissolved completely (approx. 1 minute). The mixture should be used immediately.
- For SILIKAL® RF 6200 Base, SILIKAL® Pigment must first be stirred into the resin until an homogeneous state is achieved (no lumps) and only then SILIKAL® BPO should be added and mixed until it has dissolved completely (approx. 1 minute). The mixture should be used immediately.
- Always roll on at least 600 g/m² for the first top coat layer. Optionally, after the first layer has cured, a second top coat can be rolled on with at least 500 g/m².

Guideline recipe, rollable top coat (factory pigmented)

No.	Component	Guideline recipe (% by weight)	Comment	Batch for 10 litre bucket
1	SILIKAL® RF 6200	100 %		12 kg
	Total:	100 %	Average consumption: 0.6 – 1.1 kg/m²	12 kg
2	SILIKAL® BPO	1 – 6 % with ref. to no. 1		See “Hardener dosages” table for quantities

Guideline recipe, rollable top coat with SILIKAL® RF 6200 Base

No.	Component	Guideline recipe (% by weight)	Comment	Batch for 10 litre bucket
1	SILIKAL® RF 6200 Base	90 – 95 %		10.8 – 11.4 kg
2	SILIKAL® Pigment*	5 – 10 %		0.6 – 1.2 kg
	Total:	100 %	Average consumption: 0.6 – 1.1 kg/m²	11.4 – 12.6 kg
3	SILIKAL® BPO	1 – 6 % with ref. to no. 1		See “Hardener dosages” table for quantities

* The pigment preparation (colour paste / pigment powder) must be suitable for dyeing MMA resins. Appropriate preliminary tests must be carried out to check the suitability. A compatibility table for standard pigments is given in the MMA technical documentation.

Silikal Product Information


Data sheet SILIKAL® RF 6200 / Base
Page 1 of 2

Issue MMA 7.02A – February 2023



Silikal GmbH

Ostring 23 · 63533 Mainhausen · Germany
Phone: +49 (0) 61 82 / 92 35-0
mail@silikal.de · www.silikal.de



SILIKAL® RF 6200 / Base

Reactive, pigmented, slightly elasticised top coat.

Alternatively, also available as non-pigmented, pre-filled base variant.

Characteristics as delivered

Property	Approx. value
Viscosity, +20 °C	500 mPa · s
Density, +20 °C	1.20 g/cm ³
Application temperature	0 °C to +30 °C

CE marking

CE	
09	
SILIKAL GmbH Ostring 23 · 63533 Mainhausen www.silikal.com	
RF6200-001	
EN 13813:2002	
Synthetic resin screed for application in buildings	
Reaction to fire	E ₊
Release of corrosive substances	SR
Wear resistance	≤ AR1
Bond strength	≥ 1.5
Impact resistance	≥ IR 4

CE	
09	
SILIKAL GmbH Ostring 23 · 63533 Mainhausen www.silikal.com	
System-OS8-MMA-001	
EN 1504-2:2004 1119	
ZA.1d(1.3), ZA.1f(5.1) and ZA.1g(6.1)	
Synthetic resin screed for application in buildings	
Detailed declaration of performance: www.silikal.com	



Other applicable documents

SILIKAL® BPO	Data sheet BPO
SILIKAL® Pigment	Data sheet PIG
Compatibility table, pigments	Technical documentation MMA
General notes	Technical documentation MMA
Safety data sheets	All used Silikal products

The information in this data sheet replaces all previous information about the product and its application. The application instructions as well as the technical data of the product are only guidelines. The buyer is responsible for the application and claims of third parties.

Silikal Product Information

Data sheet SILIKAL® RF 6200 / Base

Page 2 of 2

Issue MMA 7.02A – February 2023



Silikal GmbH

Ostring 23 · 63533 Mainhausen · Germany

Phone: +49 (0) 61 82 / 92 35-0

mail@silikal.de · www.silikal.de