



SILIKAL® RU 320 Pigmented

Highly flexible, pigmented reactive resin for membrane layers and waterproofing

Properties

- High viscosity
- High elasticity
- Very good crack bridging, permanent expansion capacity
- Good self-leveling properties
- Pre-filled and pigmented ready to use

Area of application

- As membrane layer for crack bridging underneath of coatings
- As waterproofing layer under toppings (tiles, coatings, with national technical test certificate (abP))

Hardener dosages

Temperature	SILIKAL® BPO % by weight *	Pot life approx. min.	Hardening time approx. min.
0 °C	6.0	20	80
+10 °C	4.0	15	60
+20 °C	2.0	15	60
+30 °C	1.0	8	40

* The amount of SILIKAL® BPO is always calculated with reference to the amount of resin.

Advice on application

- First stir well. Only after this SILIKAL® BPO should be added and mixed until it has dissolved completely (approx. 1 minute), and the mixture should be used immediately.

Guideline recipe

No.	Component	Guideline recipe (% by weight)	Comment	Batch for 10 litre bucket
1	SILIKAL® RU 320 Pigmented	100 %		10 kg
	Total:	100 %	Average consumption: 1.3 kg/m² per mm thickness	10 kg
2	SILIKAL® BPO	1 – 6 % with ref. to no. 1		See "Hardener dosages" table for quantities

Silikal Product Information

Data sheet SILIKAL® RU 320 P

Page 1 of 2

Issue MMA 7.02A – February 2023



Silikal GmbH

Ostring 23 · 63533 Mainhausen · Germany

Phone: +49 (0) 61 82 / 92 35-0

mail@silikal.de · www.silikal.de



SILIKAL® RU 320 Pigmented

Highly flexible, pigmented reactive resin for membrane layers and waterproofing

Characteristics as delivered

Property	Approx. value
Viscosity, +20 °C	2,500 mPa · s
Density, +20 °C	1.13 g/cm ³
Application temperature	0 °C to +30 °C

CE marking



Other applicable documents

SILIKAL® BPO

Data sheet BPO

General notes

Technical documentation MMA

Safety data sheets

All used Silikal products

The information in this data sheet replaces all previous information about the product and its application. The application instructions as well as the technical data of the product are only guidelines. The buyer is responsible for the application and claims of third parties.

Silikal Product Information

Data sheet SILIKAL® RU 320 P

Page 2 of 2

Issue MMA 7.02A – February 2023



Silikal GmbH

Ostring 23 · 63533 Mainhausen · Germany

Phone: +49 (0) 61 82 / 92 35-0

mail@silikal.de · www.silikal.de