

## Properties

- High strength
- High elongation capacity

## Area of application

- Reinforcing fleece for coatings or waterproofings with Silikal MMA products

## Characteristics as delivered

Property	Approx. value
Weight	110 g/m <sup>2</sup>
Tear strength lengthwise / crosswise	143 N / 346 N
Elongation lengthwise / crosswise	85% / 71%

## Advice on application

To avoid detachment, bubbles or curing problems with the MMA material, it is particularly important that the fleece is used in a wet-on-wet application. The aim of the wet-on-wet method is to completely saturate the fleece with material. This can be ensured if the membrane resin is first applied in sufficient quantity. The resin is applied evenly with a roller on a surface at least 5 cm wider than the roller width used. Immediately afterwards, the fleece is rolled into the fresh (uncured) material without bubbles and completely saturated with the remaining amount of membrane resin. After complete curing (1 – 2 hours), further coating measures can be carried out.

## Delivery form

- 1000 mm x 100 m roll
- 500 mm x 100 m roll
- 200 mm x 100 m roll
- other sizes on request

## Shelf life

Store in a dry, UV-protected and clean place! The storage stability is at least 2 years

**In addition, the respective product data sheets of the Silikal resins used must be observed!**



### Other applicable documents

General notes  
Safety data sheets

Technical documentation MMA  
All used Silikal products

The information in this data sheet replaces all previous information about the product and its application. The application instructions as well as the technical data of the product are only guidelines. The buyer is responsible for the application and claims of third parties.

## Silikal product information

Data sheet SILIKAL® TEX

Page 1 of 1

April 2025



### Silikal GmbH

Ostring 23 · 63533 Mainhausen · Germany  
Tel.: +49 (0) 61 82 / 92 35-0

mail@silikal.de · www.silikal.de